

(12)

**EUROPEAN PATENT APPLICATION**

(21) Application number: 86307816.8

(51) Int. Cl.<sup>4</sup>: **B 32 B 7/02**  
**B 32 B 27/08**

(22) Date of filing: 09.10.86

(30) Priority: 09.10.85 US 785808  
29.05.86 US 868824

(43) Date of publication of application:  
22.04.87 Bulletin 87/17

(64) Designated Contracting States:  
AT BE CH DE ES FR GB IT LI NL SE

(71) Applicant: **THE DOW CHEMICAL COMPANY**  
2030 Dow Center Abbott Road P.O. Box 1967  
Midland, MI 48640(US)

(72) Inventor: **Mott, Charles L.**  
5111 Perrine Road  
Midland Michigan 48640(US)

(74) Representative: **Raynor, John et al,**  
W.H. Beck, Greener & Co 7 Stone Buildings Lincoln's Inn  
London WC2A 3SZ(GB)

(54) Antistatic sheet material, package, and method of making.

(57) A flexible sheet material and package formed therefrom is provided. The multilayer sheet material includes a first flexible heat sealable plastic material with antistatic properties on at least the one major surface thereof which first layer is laminated to a second flexible plastic material with an electrically conductive material on the one major surface thereof and antistatic properties on the other major surface thereof.

The multilayer sheet material can include a first inner flexible, heat sealable layer having antistatic properties or intermediate layer having electrically conductive material thereon, and an outer layer of an antistatic material. Additional layers may be added.

**EP 0 219 315 A2**

ANTISTATIC SHEET MATERIAL, PACKAGE, AND METHOD OF  
MAKING

This invention relates to flexible sheet materials used for forming packages or the like for containing electrostatically sensitive components and protecting them from potentially damaging electrostatic charges, and also relates to packages  
5 formed therefrom.

As electronic components and units have  
10 become increasingly more complex, while achieving ever smaller dimensions, the problem of damage to such components due to electrostatic discharge has become of major concern. The buildup of  
15 electrostatic charges on the packages for such components can result in the discharge of a spark which can arc over or otherwise damage or destroy the  
20 components.

Similarly, the medical and pharmaceutical industries have requirements for ultraclean  
25 instruments and drug substances. Packaging of such instruments and drugs is a problem because buildup of

electrostatic charges on the packaging materials  
attracts dust and other contaminants from the air and  
surroundings. Such contaminants may become mixed  
5 with the chemicals or drugs causing purity problems.  
Likewise, when the package is opened or the product  
poured out a static charge is generated on the  
product which may attract contaminants.

10

Accordingly, a number of packages and  
packaging materials have been developed which have  
15 antistatic properties. These antistatic packages  
have found wide use in a number of industries  
including the aerospace, chemical and pharmaceutical,  
and computer and electronics industries. Such  
20 packages are designed to prevent the buildup of  
electrostatic charges on the product contained  
therein, and may also be designed to provide  
25 protection against external electric fields.

For example, many packages have been  
fabricated of plastic films or sheets compounded with  
30 or coated with antistatic additives such as  
quaternary amines, amine salts or soaps, polyethylene  
glycols or ethers, and the like. These agents act as  
35 humectants, absorbing moisture from the air, to  
reduce friction within the package and static charge  
buildup on the package. However, such antistatic  
40 agents may not be permanent (i.e., may migrate to the  
surface and be lost from the plastic) and are  
humidity dependent.

Other packages have included one or more layers of conductive material to form a protective envelope or Faraday cage-type structure about the product. A Faraday cage may be defined as an electrostatic shield composed of a continuous series of interconnected electrical conductors which surrounds a defined volume of space. Examples of packages utilizing conducting layers include Yenni Jr., et al., U.S. Patent Nos. 4,154,344 and 4,156,751; Petcavich, U.S. Patent No. 4,424,900; and Dedow, U.S. Patent Nos. 4,471,872 and 4,496,406.

However, some of these packages have no provision for closing the package, which leaves the Faraday cage protection incomplete. If adhesive tape or the like is used to close such packages, the act of stripping off the tape to reopen the package may itself create a static charge which is potentially damaging to the contents of the package. Moreover, normal flexing and handling of some prior art packages having conductive layers causes portions of the conductive layers to flake off or become ineffective. These flakes of material themselves are potential sources of contamination to the contents of the packages.

Accordingly, the need still exists in the art for a flexible packaging material and package which has permanent antistatic properties and which protects the contents thereof both from electrostatic charge buildup within the package as well as from

0219315

external electrical fields and which has a closure means to complete the Faraday cage.

5           The present invention meets that need by  
first providing a flexible sheet material which may  
be formed into a package for protecting  
electrostatically sensitive electronic components as  
10 well sensitive chemicals, ultraclean instruments or  
other materials for which the buildup of  
electrostatic charges may cause contamination or  
15 damage problems. For the purposes of this  
specification, reference to electrostatically  
sensitive components will include not only electronic  
parts and devices, but also sensitive chemicals and  
20 pharmaceuticals as well as other materials or  
instruments which have the potential of being damaged  
or contaminated by an electrostatic buildup or  
25 discharge.

          According to one aspect of the present  
invention, a multilayer flexible sheet material is  
30 provided which includes a first layer of a flexible  
heat sealable plastic material having primary and  
secondary major surfaces. Antistatic properties are  
35 present on at least the secondary major surface of  
this layer. The sheet material also includes a  
second layer of flexible plastic also having primary  
and secondary major surfaces. An electrically  
40 conductive material is on the primary major surface  
and antistatic properties are present on at least the  
secondary major surface of this second layer. The

layers are bonded together along their respective primary major surfaces, preferably with a suitable adhesive.

5           According to another aspect of the present invention, a multilayer flexible sheet material is provided which includes an inner layer of a flexible  
10 heat sealable plastic. The inner layer may be, for example, a polyolefin or thermoplastic polyurethane. A second intermediate layer may be, for example, a  
15 polyester such as polyethylene terephthalate or a copolymer of ethylene and acrylic acid or vinyl acetate. The second layer has electrically  
20 conductive material deposited thereon. An outer layer of an antistatic material is coated over the second layer or, alternatively, antistatic material may be incorporated into a polymer which is in turn  
25 coated over or laminated to the second layer.

          Antistatic properties may then be imparted to the first layer by passing the laminate through an  
30 electron beam curing process. Alternatively, antistatic properties for the first layer can be achieved by coating an antistatic material onto the  
35 first layer, incorporating an antistatic material into the polymer material of the first layer, or incorporating an antistatic material into a polymer  
40 which in turn is coated over or laminated to the first layer.

          According to another aspect of the present invention, a multilayer flexible sheet material is

provided which includes a first layer of a flexible heat sealable plastic material. Antistatic properties are present on at least the first layer. Again, these antistatic properties can be achieved by the procedures discussed above. The sheet material also includes a third layer of flexible plastic also having primary and secondary major surfaces.

A second intermediate layer having an electrically conductive material thereon is sandwiched between the first layer and the primary surface of the third layer. In one embodiment, the first, and/or second, and/or third layers are bonded together with a suitable adhesive.

The flexible sheet material can be readily formed into a package either by folding a sheet onto itself and heat sealing the opposing edges or superimposing two sheets and sealing the opposing edges. Additionally, a closure device may be attached to or incorporated in the package. A preferred closure means is a releasable interlocking plastic zipper, the opposing rib and groove elements of which may be laminated to opposing inner faces of the sheet material adjacent the open end of the package.

A preferred method for fabricating the package includes the steps of providing a first layer of a flexible heat sealable plastic material as described above and coating the surface of the first layer or the primary major surface of the first layer

with an antistatic material which comprises an acrylate monomer-oligomer mixture containing an alkylether triethyl ammonium sulfate. The antistatic material is cured by exposure to an electron beam. A second layer of flexible plastic material is also provided which has primary and secondary major surfaces. An electrically conductive material such as a metal is deposited on the primary major surface. The deposition may be carried out using well known vacuum deposition or sputtering techniques. Alternatively, a number of conductive materials in sheet or web form are readily commercially available and may be used.

The first and second layers of the flexible sheet may be joined together by coating one or both of these surfaces with either a thermoplastic or thermosetting adhesive and pressing the first and second layers together. The thermosetting adhesive is then cured by exposing it to an electron beam. Surprisingly, curing by exposure to an electron beam causes both exterior facing surfaces of the multilayer flexible sheet material to possess the effect of antistatic properties. This phenomenon occurs both during the initial curing of the antistatic material and again during electron beam curing of the adhesive. Optionally, additional antistatic material may be coated onto the outside of the package to insure optimum performance of the package structure in dissipating static charges.



0219315

Alternatively, the antistatic material and adhesive material may be blended together and applied to one or both of the first and second layers and  
5 cured simultaneously by exposure to an electron beam. However, it has been found that such a system does not product as good a result (in terms of the  
10 strength of the antistatic properties on both secondary major surfaces) as does the preferred process. In yet another alternative embodiment,  
15 techniques other than electron beam exposure may be utilized to provide antistatic properties on both secondary major surfaces of the layers. For example,  
20 an antistatic material can be compounded into one or both of the layers, and the layers joined using conventional lamination techniques.

25 The flexible sheet material and process for making it provide a flexible packaging material and package which has permanent antistatic properties on both the interior and exterior facing surfaces of a  
30 package. The metal layer is embedded in the multilayer structure and cannot flake off or peel when the package is flexed. It provides a Faraday  
35 cage to protect the contents of the package from external electric fields. The optional zipper closure means, which may also contain an antistatic  
40 agent and/or semiconductive filler, secures the contents of the package from accidental spillage and brings the opposing faces of the open end of the package into close physical contact which enhances

0219315

the Faraday cage protection. The result is a package which has permanent antistatic properties, is non-volatile, non-sluffing, non-humidity dependent, and otherwise offers a number of advantages over pre-existing antistatic packages.

Accordingly, the present invention provides a flexible sheet material, package, and process for making one which has permanent antistatic properties and protects the contents of the package from both electrostatic charge buildup within the package as well from external electric fields. The advantages of the invention will become apparent from the following detailed description, the accompanying drawings, and the appended claims.

Fig. 1 is a perspective view of a package formed in connection with the teachings of the present invention;

Fig. 2 is a cross-sectional view taken along line 2-22 in Fig. 1 illustrating in detail the optional zipper closure for the package;

Fig. 3 is an enlarged cross-sectional view through the sheet material used to form the package of Fig. 1;

Fig. 3A is an enlarged cross-sectional view through one embodiment of the sheet material used to form the package of Fig. 1;

Fig. 4 is an enlarged cross-sectional view through another embodiment of the sheet material used to form the package of Fig. 1;

0219315

Fig. 5 is an enlarged cross-sectional view through another embodiment of the sheet material used to form the package of Fig. 1;

5 Fig. 6 is an enlarged cross-sectional view through another embodiment of the sheet material used to form the package of Fig. 1;

10 Fig. 7 is an enlarged cross-sectional view through yet another embodiment of the sheet material used to form the package of Fig. 1; and

15 Fig. 8 is an enlarged cross-sectional view through still yet another embodiment of the sheet material used to form the package of Fig. 1.

20 Referring now to Fig. 1, there is illustrated a package 10 which is the preferred form of package formed in accordance with the present invention.

Other package, bag, pouches, and forms, including  
25 thermoformed containers and laminated containers, may be prepared from the flexible sheet material of the present invention. Package 10 is shown as generally  
30 rectangular in shape, but may be formed into any convenient shape or size depending on the component or material to be contained therein. Package 10 includes two opposing walls 12 and 14 which comprise  
35 the multilayer flexible sheet material of the present invention described in greater detail below. In the preferred embodiment, package 10 is formed by  
40 applying releasable and reclosable closure 24 to a web of the flexible sheet material, and folding the web of the flexible sheet material upon itself at fold line 16 to bring complementary rib and groove

:

0219315

elements 26 and 28 into alignment. Opposing edges 18 and 20 are then heat sealed together and packages 10 severed from the web in a conventional manner.

5           As schematically illustrated in Fig. 2, closure 24, adjacent opening 22, comprises an interlocking zipper having complimentary rib and  
10 groove elements 26 and 28, respectively. While single rib and groove elements have been illustrated for simplicity, it will be apparent to those skilled  
15 in the art that other structures such as so-called Wide Track zippers with a plurality of complimentary rib and groove elements may be used as described in  
20 Published British Patent Application No. 2133462 published July 25, 1984. Optional closure 24 is preferably extruded or laminated onto the sheet material prior to the formation of package 10.  
25 Preferably, an antistatic material and/or semiconductive filler is incorporated into closure 24.

30           Closure 24 may be used to enhance the Faraday-cage effect of the package by providing a electrical path through the zipper to opposite walls of the package. Preferably, closure 24 has a surface  
35 resistivity in the range of from  $10^{13}$  to  $10^2$  ohms/sq. Closure 24 is located approximately 0.24 to 4 inches (0.6 to 10.2 cm), and preferably 0.5 to 1.5 inches  
40 (1.2 to 3.8 cm), from open end 22 of package 10. Closure 24 may be omitted, or alternate closure means used, if so desired.

0219315

One embodiment of the multilayer flexible sheet material of the present invention which is used to form walls 12 and 14 of package 10 is illustrated in enlarged cross section in Fig. 3 and Fig. 3A. The legends "Inside" and "Outside" have been added to the drawing to aid in the understanding of the invention. The side of the material labeled "Inside" is the inwardly facing surface of the material designed to be in contact with the contents of package 10 which is formed as described above. The "Inside" may also have closure 24 applied to it as illustrated in Fig. 2. The side of the material labeled "Outside" is the exterior or outwardly facing surface of the multilayer material.

In the embodiment illustrated in Fig. 3, the sheet material is formed by the lamination of two principal layers. First layer 30 is formed of a flexible heat sealable plastic having primary and secondary major surfaces 32 and 34, respectively. First layer 30 has an antistatic material 36 on its primary major surface 32. First layer 30 also has antistatic properties (illustrated by numeral 36") on at least secondary major surface 34. By "antistatic" material or agent, it is meant that the material or agent has properties which prevent the buildup of or cause the dissipation of static charges. Antistatic material 36 provides a surface conductivity in the range from about  $10^6$  to about  $10^{13}$  ohms/sq., and preferably about  $10^8$  to about  $10^{11}$  ohms/sq.

First layer 30 is preferably a polyolefin such as polyethylene (either high or low density, branched or linear) or polypropylene. Additionally,  
5 layer 30 may be a copolymer of ethylene or propylene with a copolymerizable monomer. Preferred copolymers include copolymers of ethylene with either vinyl  
10 alcohol or vinyl acetate, ethylene-acrylic acid copolymers, and ethylene-carbon monoxide copolymers. Layer 30 may also comprise blends or mixtures of  
15 these polyolefin homopolymers and copolymers.

Alternatively, first layer 30 need not be a polyolefin but simply be a heat sealable plastic such  
20 as a heat sealable polyester. One example of such a material is polyethylene terephthalate glycol (PETG). Additionally, first layer 30 need not be a single  
25 unitary layer but may be comprised of a number of plies as long as the ply adjacent the "Inside" surface of the laminate, i.e., secondary major surface 34 is heat sealable. Thus, it may be  
30 desirable to incorporate other polymers having properties such as toughness, resistance to penetration, chemical resistance, or the like into  
35 first layer 30. For example, a nylon ply can be incorporated with one or more polyolefin plies to impart additional toughness to layer 30. This nylon  
40 ply may be coextruded with a polyethylene ply or otherwise laminated thereto, or alternatively may be sandwiched between two polyethylene plies.

Second layer 38 is formed of a flexible plastic having primary and secondary major surfaces 40 and 42, respectively. Second layer 38 has  
5 deposited on its primary major surface 40, a layer of an electrically conductive material 44. The secondary major surface 42 has antistatic properties  
10 illustrated by numeral 36'.

Layer 38 is preferably a polyester, but may also be a polyolefin such as polyethylene or  
15 polypropylene polymers or copolymers or other polymeric materials. Additionally, layer 38 may comprise blends or mixtures of such polymers, or may  
20 include two or more plies of coextruded polymers.

Electrically conductive layer 44 is preferably formed by depositing a thin layer of metal  
25 on primary major surface 40 of layer 38. This deposition may be accomplished through the use of conventional vapor deposition or sputtering  
30 techniques. Preferred metals include aluminum, stainless steel, nickel, copper, and mixtures thereof. The primary major surface 40 of layer 38  
35 may be pretreated to render it more receptive to metallization. Optionally, electrically conductive layer 44 may be a coated or laminated metal grid, a metal filled plastic film, or other conductive  
40 material.

Layer 44, if vacuum deposited or sputtered, is preferably about 50 to about 200 Angstroms thick,

:

and most preferably about 100 Angstroms thick. Its surface resistivity is preferably about 100 ohms/sq. The coating may be discontinuous and/or have pinholes therein with no substantial adverse effect on the Faraday-cage structure which results when the package is formed.

10 Alternatively, metallized polyester films and sheets are readily commercially available from a number of suppliers and may be utilized in the practice of the present invention. It is preferred that the combination of layers 38, 44 and 30 be partially transparent or transparent to permit visual inspection of the contents of the package without the need for opening the package. Opening of the package outside of a controlled environment which allows for discharge of any static charge buildup may be detrimental. Accordingly, the ability to make a visual inspection of a packaged component, including any part or control numbers included in the package, is desirable. It is also possible to have one wall of the package partially transparent or transparent (through which the component may be inspected) and the other wall opaque. For example, a cushioning layer, such as a foamed plastic film, may be laminated to, or included in, wall 12 or 14 while the other wall remains as described. In the preferred embodiment where both walls are transparent, the walls of package 10 are made up of the two principal layers. The two layers 30 and 38 are bonded together along their respective primary major surfaces through



0219315

the use of an adhesive 46. Adhesive 46 is preferably a thermosetting epoxy or urethane adhesive which is curable by exposure to an electron beam. Further, it is desirable that the adhesive be a solvent-free, 100 percent solids material; although other forms of adhesive may be used.

10 In the embodiment illustrated in Fig. 3A, the sheet material may be formed by an extrusion-coating process. This offers a number of advantages over processes which involve lamination steps. First layer 32 is formed of a flexible heat sealable plastic. Second layer 34 is coextruded with first layer 32. An electrically conductive layer 44 is deposited on second layer 34. An antistatic material 36 is coated over conductive layer 44. By "antistatic" material or agent, it is meant that the material or agent has properties which prevent the buildup of or cause the dissipation of static charges. Antistatic material 36 provides a surface conductivity in the range from  $10^6$  to  $10^{13}$  ohms/sq., and preferably  $10^8$  to  $10^{11}$  ohms/sq. First layer 32 also has antistatic properties (illustrated by numeral 36") on its "Inside" surface. Such antistatic properties may be created by electron beam curing antistatic material 36 to cause antistatic properties 36" to appear on the Inside surface of layer 32.

Alternatively, antistatic properties 36" can be achieved by coating an antistatic material onto

first layer 32, incorporating an antistatic material into the polymer which makes up first layer 32, or incorporating an antistatic material into a polymer which in turn is coated over or laminated to first layer 32. For example, a thermoplastic polyurethane having antistatic properties may be coated over or laminated to first layer 32.

10

As mentioned layers 32 and 34 are preferably coextruded ones, although other known methods of providing those layers may be utilized. First layer 32 is a heat sealable material and is preferably a polyolefin such as polyethylene (either high or low density, branched or linear) or polypropylene homopolymers or copolymers. First layer 32 may also include copolymers of ethylene and vinyl acetate, copolymers of ethylene and carbon monoxide, copolymers of ethylene and acrylic acid and blends or mixtures of such polyolefins. Alternatively, first layer 32 may be a thermoplastic polyurethane.

30

Second layer 34 is preferably a copolymer of ethylene and acrylic acid or vinyl acetate. Alternatively, second layer 34' (as shown in Figs. 4 and 8) may be a polyester such as polyethylene terephthalate. While electrically conductive materials such as metals will not bond or adhere directly to a polyurethane or polyolefin such as polyethylene, it has been found that such conductive materials will bond directly to ethylene-acrylic acid

35

40

copolymers, ethylene-vinyl acetate copolymers, and polyesters.

5 Preferably, layer 32 is a blend of about 0-25 percent high density polyethylene and 25 percent - 100 percent linear low density polyethylene, by weight, and second layer 34 is a copolymer of 10 ethylene and from 2-15 percent, and more preferably 2-5 percent, acrylic acid. A material such as preferred layers 32, 34 is a coextruded material 15 commercially available from The Dow Chemical Company under the designation Dow Adhesive Film. Additionally, the laminate may comprise an additional number of layers as long as the layer adjacent the 20 "Inside" surface of the laminate, i.e., layer 32, is heat sealable, there is an intermediate layer 34 bearing a electrically conductive layer 44 and there 25 is an outer layer 36 of antistatic material or a material having antistatic properties.

30 Thus, it may be desirable to incorporate other polymers having properties such as toughness, resistance to penetration, chemical resistance, or the like into the laminate. For example a nylon 35 layer 33 (Fig. 6) or a polyurethane layer 33' (Figs. 5 and 7) may be incorporated. Likewise, adhesive layers 46 (Figs. 4 and 8) and 46' (Fig. 8) may also 40 be used, preferably when second layer 34' is a polyester.

The preferred antistatic material for use in the present invention is an acrylate monomer-oligomer

5 mixture containing an alkylether triethyl ammonium  
sulfate available from Metallized Products, Inc.,  
Winchester, Massachusetts, under the name Staticure.  
the material is curable by exposure to an electron  
beam and cures to a permanent, nonbleeding coating  
which is not dependent on humidity for its antistatic  
effect. Further details concerning this antistatic  
10 material may be found in British Patent Application  
No. 2,156,362, published October 9, 1985.

15 Alternatively, other known antistatic agents  
such as quaternary ammonium compounds or carbon may  
be utilized. These antistatic agents may be  
compounded with the polymers making up one or more  
20 layers of the sheet material, may be coated onto  
respective "Inside" and/or "Outside" surfaces of the  
sheet material, or may be compounded with a polymer  
25 which is then itself coated onto the respective  
"Inside" and/or "Outside" surfaces of the sheet  
material.

30 Electrically conductive layer 44 is  
preferably formed by depositing a thin layer of metal  
on layer 34 or 34'. This deposition may be  
35 accomplished through the use of conventional vapor  
deposition or sputtering techniques. Preferred  
metals include aluminum, stainless steel, nickel,  
40 copper, and mixtures thereof. Layer 34 or 34' may be  
pretreated to render it more receptive to  
metallization. Optionally, electrically conductive  
layer 44 may be a coated or laminated metal grid or

0219315

mesh, a metal filled plastic film, or other  
conductive material.

5           Layer 44, if vacuum deposited or sputtered,  
is preferably 50 to 200 Angstroms thick, and most  
preferably 100 Angstroms thick. Its surface  
resistivity is preferably about 100 ohms/sq. The  
10 coating may be discontinuous and/or have pinholes  
therein with no substantial adverse effect on the  
Faraday-cage structure which results when the package  
is formed.  
15

          It is preferred that the combination of  
layers in the laminate be partially transparent or  
20 transparent to permit visual inspection of the  
contents of the package without the need for opening  
the package. Opening of the package outside of a  
25 controlled environment which allows for discharge of  
any static charge buildup maybe detrimental.  
Accordingly, the ability to make a visual inspection  
of a packaged component, including any part or  
30 control numbers included in the package, is  
desirable. It is also possible to have one wall of  
the package partially transparent or transparent  
35 (through which the component may be inspected) and  
the other wall opaque. For example, a cushioning  
layer, such as a foamed plastic film, may be  
40 laminated to, or included in, wall 12 or 14 while the  
other wall remains as described. In the preferred  
embodiment where both walls are transparent, the

walls of package 10 are made up of the two principal layers.

5 In the alternative embodiment illustrated in Fig. 4, where like elements are identified by like reference numerals, the sheet material comprises a first layer 32, a second layer 34', and a conductive  
10 layer 44.

Second layer 34' is formed of a flexible plastic having primary and secondary major surfaces  
15 40 and 42, respectively. Second layer 34 has deposited on its primary major surface 40, a layer of an electrically conductive material 44. The  
20 secondary major surface 42 has antistatic properties illustrated by numeral 36'.

In this instance second layer 34' is  
25 preferably a polyester, but may also be a thermoplastic polyurethane or a polyolefin such as polyethylene or polypropylene polymers or copolymers,  
30 including copolymers of ethylene and acrylic acid or vinyl acetate. Additionally, layer 34' may comprise blends or mixtures of such polymers, or may include  
35 two or more plies of coextruded polymers. Optional layer 38 may be a copolymer of ethylene and acrylic and or vinyl acetate in which case layers 32 and 38,  
40 like layers 32 and 34 of Fig. 3A, may be coextruded material available from the Dow Chemical Company under the designation Dow Adhesive Film.

The two layers 32 and 34' may be bonded together along their respective primary major surfaces through the use of an adhesive 46. Adhesive 5 46 is preferably a thermosetting epoxy or urethane adhesive which is curable by exposure to an electron beam. Adhesive 46 may also be a thermoplastic 10 adhesive and may have an antistatic material incorporated in it. Further, it is desirable that the adhesive be a solvent-free, 100 percent solids 15 material although other forms of adhesive may be used.

Alternatively, conductive layer 44 may be 20 bonded directly to layer 38 by hot roll lamination or as described above, with respect to the embodiment illustrated in Fig. 3A.

25 Thus, a preferred method of making the multilayer flexible sheet material of the embodiment illustrated in Fig. 4 and Fig. 3 includes the 30 following steps. Layer 32 (layer 30 in Fig. 3) is coated with antistatic material 36, and the antistatic material is cured by exposure to an 35 electron beam. During this curing step antistatic properties are produced on both major surfaces of layer 32 (layer 30 in Fig. 3). This phenomenon is 40 discussed in "EB-curable Coating" Is Clear Cure For Static", Converting Magazine, March 1985, and "Electron Beam Radiation Cured Coatings for Static Control", Evaluation engineering, September 1985. That is, the "Inside" surface (surface 34 in Fig. 3)

of layer 30, following curing of antistatic material 36, now shows antistatic properties (illustrated by numeral 36") even though no antistatic material was originally coated directly thereon. Of course, it is possible in an additional step to also coat antistatic material on the "Inside" surface (surface 34 in Fig. 3) of layer 32.

Second layer 34' (layer 38 in Fig. 3), with electrically conductive layer 44 thereon, is then joined with layer 32 (layer 30 in Fig. 3) using adhesive 46. As described above, electrically conductive layer 44 may be deposited on layer 34' (layer 38 in Fig. 3) by sputtering or vacuum deposition. Alternatively, a metallized plastic which is commercially available may be utilized.

Adhesive 46 may be applied either to electrically conductive layer 44 or antistatic material 36 or both. It is preferably applied by a gravure coating process, although it may be sprayed or otherwise coated using conventional techniques which are suitable for coating 100 percent solids materials. After application of adhesive 46 and lamination of layers 32 and 34' (layers 30 and 38 in Fig. 3) using pressure rolls or the like, the laminate is again exposed to an electron beam to cure the adhesive. This second curing step causes antistatic properties to appear on the "Outside" surface 42 of layer 34' (exterior facing surface 42 of layer 38 in Fig. 3). Surface 42, following curing



0219315

of the adhesive 46, now shows antistatic properties (illustrated by numeral 36') even though no antistatic material was originally coated directly thereon. Again, it is possible in an additional step to coat antistatic material on surface 42.

In an alternative procedure, antistatic material 36 may be blended with adhesive 46 and applied to one or both layers. then, a single curing step utilizing an electron beam is performed which cures adhesive 46 and results in antistatic properties appearing on both the inner and exterior faces of the laminated sheet material; although, as mentioned, the results achieved with this alternative procedure are not as good as those achieved with the preferred process.

As mentioned, the preferred method for making the sheet material of the embodiment illustrated in Fig. 3A is advantageous in that no adhesive or lamination is required. First layer 32 and second layer 34 are coextruded second layer 34 has deposited thereon electrically conductive layer 44 using a suitable vacuum deposition or sputtering technique. Layer 44 will bond to layer 34 of an ethylene-acrylic acid or ethylene-vinyl acetate copolymer. Then, a layer of antistatic material 36 is coated onto layer 44 in the manner described above. The antistatic material 36 is then cured utilizing an electron beam. The curing step causes antistatic properties to appear on the "Inside" facing surface of layer 32,

illustrated by numeral 36", even though no antistatic material was originally coated directly thereon.

Again, as discussed previously, an additional coating step may be performed to apply antistatic material on the "Inside" facing surface of layer 32. That process is illustrated by Example 2.

10           The structures shown in Figs. 5 and 7 are similar to the one shown in Fig. 3A except that a layer 33' is included. Preferably polyurethane layer 15 33' is a thermoplastic polyurethane which may be hot roll laminated over conductive layer 44 (Fig. 5) prior to being coated with antistatic material 36 or hot roll laminated to thermoplastic layer 32 20 (Fig. 7). In the latter instance, thermoplastic polyurethane layer 33' serves as the "Inside" heat sealable layer. Alternatively, the layers 44 and 32 25 can be interchanged.

          The structure shown in Fig. 6 is also similar to that of Fig. 3A except that a third layer 33, 30 which may be nylon for example, is preferably coextruded along with, and between, layers 32 and 34.

35           The structure shown in Fig. 8 is similar to the one shown in Fig. 4 except that an additional heat sealable layer 32' is adhered over second layer 34" by use of adhesive 46'. In a "sandwich" 40 structure of that type, either surface may be used as the "Outside" or "Inside" because both outer layers of the laminate are a heat sealable layer (32 or 32') having antistatic properties (36 or 36').

In order that the invention may be more readily understood, reference is made to the following examples, which are intended to illustrate the invention but are not to be taken as limiting the scope thereof.

10

Example 1

15 Preparation of First Layer 30 (Figure 3)

A common insulative low density 2 mil (0.05 mm) polyethylene film was gravure coated on one side with Staticure antistatic electron beam curable coating from Metallized Products to an approximate 0.1 mil (0.0025 mm) thickness. The coated film was immediately passed through an electron beam (Energy Sciences curtain type) at 200 ft./min. (1.02 m/s) and exposed to 3 megarads (0.03 megagrays).

30 Measurement of surface resistivity according to (ASTM D-257 method) of the uncoated film originally was greater than  $10^{14}$  ohms per square on both surfaces (insulative).

35 The surface resistivity after coating and electron beam treatment was measured to be  $2.3 \times 10^{11}$  ohms per square (inner surface) and  $5.5 \times 10^{10}$  ohms per square (outer surface).

0219315

Preparation of Second Layer 38 (Figure 3)

5 A one mil (0.025) polyester (polyethylene  
terephthalate (mylar) film was coated with aluminum  
at a controlled density of 100 angstroms resulting in  
a partially transparent metallized film with surface  
10 resistivity of 100 ohms per square on the metallized  
surface and greater than  $10^{14}$  ohms per square on the  
non-metallized surface.

15 Preparation of Laminated Flexible Sheet Material

The aluminum side of the polyester was  
20 gravure coated to an approximate thickness of 0.1 mil  
(0.025 mm) with a thermoset electron beam curable  
adhesive (epoxy type). The previously coated side of  
the polyethylene film in step 1 was now brought in  
25 contact with the adhesive and both films passed  
through nip rolls at ambient temperature which fed  
the two now joined films through an electron beam  
30 curtain (3 megarads) at 200 ft./min. (1.02 m/s).

The laminated film structure was wound on a  
core prior to subsequent conversion. The resultant  
35 material is represented in Figure 3. Surface  
resistivity measurements [ASTM D-257 method] on the  
polyester outer surface was measured to be  $2 \times 10^{12}$   
40 ohms/square. The surface resistivity was measured on  
the inner heat seal surface and found to be  $3 \times 10^{12}$   
ohms/square.

Preparation of Package 10

5       The above mentioned film was now placed on an  
unwind stand for subsequent application of closures  
on the heat sealable inside surface. The cross  
section of the final closure was represented  
10       schematically in Figure 2. The film web was threaded  
through a series of rolls to avoid wrinkles. Low  
density polyethylene resin previously compounded to  
contain an antistat agent such as Armostat 350 was  
15       extruded through dies designed to result in closures  
shaped similar to rib element 26 and the other groove  
element 28 of Figure 2 and onto the unheated heat  
20       seal layer side of the film mentioned.

      The web (walls 12 and 14), now containing  
both rib element 26 and groove element 28 was folded  
25       and joined at the closure prior to side seam heat  
sealing and cutting into bags. Bar type heat seals  
were utilized for side seam seals with a temperature  
30       range of 230° to 330°F (110° to 165.6°C) and packages  
10 were severed from the web. No further work was  
required to the product and it was now ready for use.

35

Example 2

40       A package adapted to receive and protect an  
electrostatically sensitive component was produced in  
accordance with the present invention as follows. A  
three mil (0.076 mm) thick flexible two-ply film was

0219315

selected for use as the inner layer of the package. One ply of the film comprised a copolymer of ethylene and from 2 to 5 percent acrylic acid while the other  
5 ply of the film was a polyethylene homopolymer. The film had a surface resistivity on both surfaces of greater than  $10^{14}$  ohms/square.

10 The ethylene-acrylic acid copolymer surface was vacuum metallized with aluminum using a controlled density, wire wound vacuum metallization  
15 technique. The final coating thickness was approximately 100 Angstroms. The aluminum layer had a surface resistivity of 50 to 100 ohms/square. The aluminum layer had 40 to 60 percent light  
20 transmission characteristics.

The aluminum layer was then coated with a  
25 radiation curable 100 percent solids acrylate monomer-oligomer mixture which contained 15 parts by weight of a triethyl-alkyl ether ammonium sulfate antistatic agent (commercially available from Emery  
30 Industries under the designation Emerstat 6660). The mixture was applied by a gravure coating process to a coat weight of 0.5-2.0 lbs./ream. The coating on the  
35 film was then exposed to radiation by an electron beam. The electron beam was applied by an Energy Sciences curtain-type device. The film traveled  
40 under the electron beam at a speed of 200 feet/minute (1.02 m/s) at an exposure of 3 megarads. The film was then rewound onto a mill roll.

34,157A-F

-29-

After subsequent aging on the roll, surface resistivities on both surfaces of the film were measured. The antistatic coated surface of the film exhibited a resistivity of less than  $1 \times 10^{12}$  ohms/square, while the uncoated surface exhibited a resistivity of less than  $1 \times 10^{13}$  ohms/square.

5  
10 Additionally, the time to dissipate a positive or negative 5000 volt static charge to 50 volts was measured. The film, prior to being coated with the  
15 antistatic agent, took more than 3 minutes to dissipate a 5000 volt charge, while the coated film took less than 0.4 seconds to dissipate the same charge.

20

The coated film, as produced above, was then unwound for fabrication into packages. Mating rib  
25 and groove fasteners were extruded from low density polyethylene and then applied to opposing inner heat sealable surfaces of the film as taught in copending U.S. Application Serial No. 753,191, filed July 9,  
30 1985, and assigned to the same assignee as the present invention. The cross-section of the final closure elements is represented schematically in  
35 Figure 2. Application of the fastener elements was accomplished by threading the film through a series of rolls to avoid wrinkles. The low density  
40 polyethylene resin, which had been compounded to contain an antistatic agent such as Armostat 350 was extruded onto the unheated inner heat sealable film surfaces.

0219315

5 The web (walls 12 and 14), now containing  
both rib element 26 and groove element 28, was then  
folded and joined at the fasteners prior to side seam  
heat sealing and severing into individual zippered  
packages. Bar-type heat seals were used for side  
seam seals with a temperature range of 230° to 330°F  
10 (110° to 165.5°C) and packages 10 were severed from  
the film web.

15

Example 3

20 A thermoplastic urethane polymer, prepared in  
accordance with copending U.S. Application Serial  
No. 785,294, filed October 7, 1985, and assigned to  
the same assignee as the present invention, was  
25 compounded with an antistatic agent. The antistatic  
agent is 1.0 percent by weight sodium thiocyanate.  
The polymer was then fabricated into a film having a  
30 thickness of 2.5 mils (0.06 mm). The surface  
resistivity of the film was measured to be less than  
 $10^{12}$  ohms/square.

35

The urethane polymer film was then laminated  
to the metallized film of Example 2. The urethane  
film was joined to the metallized surface of the film  
40 by hot roll lamination resulting in a laminate as  
illustrated in Figure 5. Zipper fastener profiles  
were extruded from the same urethane polymer onto the  
laminated structure by the process taught in

34,157A-F



0219315

compending U.S. Application Serial No. 753,191, filed July 9, 1985, and assigned to the same assignee as the present invention.

5           The laminated structure was formed into individual packages as previously described in Example 2. The resulting packages exhibited good  
10 puncture and abrasion resistance. Such packages are especially useful to protect electronic circuit boards and other electronic components having exposed  
15 wire ends.

          Having described the invention in detail and by reference to preferred embodiments thereof, it  
20 will be apparent that modification and variations are possible without departing from the scope of the invention defined in the appended claims.

25

30

35

40

34,157A-F

1. A flexible sheet material adaptable for forming a package, bag, pouch, or the like for containing electrostatically sensitive components comprising;

(a) a first layer of a flexible heat sealable plastic material having primary and secondary major surfaces with antistatic properties on at least said secondary major surface thereof; and

(b) a second layer of a flexible plastic material having primary and secondary major surfaces with an electrically conductive material on said primary major surface and with antistatic properties on at least said secondary major surface, said first and second layers of material being bonded together along said primary major surfaces, respectively, of said first and second layers.

2. The flexible sheet material of Claim 1 further including an antistatic material on said primary major surface of said first layer.

3. The flexible sheet material of Claim 1 in which said first layer is selected from the group

consisting of polyethylene, polypropylene, copolymers  
of ethylene or propylene with a copolymerizable  
monomer, polyethylene terephthalate glycol and blends  
5 or mixtures thereof.

4. The flexible sheet material of Claim 1  
in which said first layer comprises a plurality of  
10 plies of polymeric materials, with at least one of  
said plies comprising nylon, and with the further  
proviso that the polymeric material forming said  
15 second major surface of said first layer is heat  
sealable.

5. The flexible sheet material of Claim 1  
20 in which said second layer is selected from the group  
consisting of polyethylene and polypropylene polymers  
and copolymers, polyester, and blends of mixtures  
25 thereof.

6. The flexible sheet material of Claim 1  
in which said first and second layers are bonded  
30 together with a thermosetting adhesive.

7. The flexible sheet material of Claim 6  
in which said thermosetting adhesive contains an  
35 antistatic material.

8. A flexible sheet material adaptable for  
40 forming a package, bag, pouch, or the like for  
containing electrostatically sensitive components  
comprising:

(a) a first inner layer of a flexible plastic material, said first inner layer being heat sealable,

5 (b) a second intermediate layer having an electrically conductive material deposited thereon, and

10 (c) an outer layer of an antistatic material, said outer layer being located on the side of said second layer opposite said first inner layer.

15 9. The flexible sheet material of Claim 8 in which said inner layer has antistatic properties.

20 10. The flexible sheet material of Claim 9 in which said inner layer is a polyolefin or thermoplastic polyurethane and said second layer is a copolymer of ethylene and acrylic acid or vinyl acetate.

25 11. The flexible sheet material of Claim 10 in which said first and second layers are formed by a coextrusion process.

30 12. The flexible sheet material of Claim 9 including a third layer comprising nylon said third layer being sandwiched between said second and first layers.

35 13. A flexible sheet material adaptable for forming a package, bag, pouch, or the like for containing electrostatically sensitive components comprising:

(a) a first inner layer of a flexible, heat sealable plastic material having antistatic properties;

5 (b) a second layer of a flexible plastic material having an electrically conductive material deposited thereon; and

10 (c) a layer of adhesive between said first layer and said second layer bonding said first layer to said second layer, and

(d) an outer antistatic surface, and outer  
15 surface being located on the side of said second layer opposite said first inner layer.

20 14. The flexible sheet material of Claim 13 in which said first layer is a polyolefin and said second layer is a polyester.

25 15. ~~The~~ flexible sheet material of Claim 11 including a ~~third~~ layer which is selected from the group consisting of films of polyester, polyolefin polymers or copolymers, thermoplastic polyurethane,  
30 copolymers of ethylene with acrylic acid or vinyl acetate, and blends.

35 16. The flexible sheet material of Claim 15 in which said second layer is bonded to said third layer with an adhesive.

40 17. The flexible sheet material of Claim 1, 8 or 13 in which said electrically conductive material is selected from the group consisting of

aluminum, stainless steel, nickel, copper, and mixtures thereof.

5 18. The flexible sheet material of Claim 13 including a layer of antistatic material.

10 19. The flexible sheet material of Claim 2, 9 or 18 wherein said antistatic material is cured acrylate monomer-oligomer mixture containing an alkylether triethyl ammonium sulfate.

15 20. A package adapted to receive and protect an electrostatically sensitive component, the walls of said package formed of a flexible sheet material of Claim 1, 8 or 13.  
20

21. The package of Claim 20 including releasable, interlocking closure means on opposing  
25 inner faces of one end of said walls.

22. A method of fabricating a multilayer flexible sheet material adaptable for forming a  
30 package, bag, pouch, or the like for containing electrostatically sensitive components comprising the steps of:

35 (a) providing a first layer of a flexible, electrically insulating, heat sealable plastic material having primary and secondary major surfaces;

40 (b) coating said primary major surface of said first layer with an antistatic material comprising an acrylate monomer-oligomer mixture containing an alkylether triethyl ammonium sulfate;

(c) curing said antistatic material by exposing it to an electron beam;

5 (d) providing a second layer of a flexible plastic material having primary and secondary major surfaces with an electrically conductive material deposited on said primary major surface;

10 (e) joining said first and second layers along their primary major surfaces by coating one or both of said primary major surfaces with a thermosetting adhesive and pressing said first and  
15 second layers together; and

(f) curing said thermosetting adhesive by exposing it to an electron beam, said curing steps  
20 causing said antistatic material to provide antistatic properties to said secondary major surfaces of said layers.

25 23. A method of fabricating a multilayer flexible sheet material adaptable for forming a package, bag, pouch, or the like for containing  
30 electrostatically sensitive components comprising the steps of:

(a) providing first inner layer of a flexible, heat sealable plastic material and a  
35 coextruded second layer of flexible plastic material,

(b) depositing an electrically conductive material on said second layer,

40 (c) coating an outer layer of antistatic material over said electrically conductive material, said antistatic material comprising an electron beam curable mixture, and

(d) curing said antistatic material by exposing it to an electron beam, said curing step causing said antistatic material to provide  
5 antistatic properties to said first inner layer.

24. A method of fabricating a multilayer flexible sheet material adaptable for forming a  
10 package, bag, pouch, or the like for containing electrostatically sensitive components comprising the steps of:

15 (a) providing a first layer of a flexible heat sealable plastic material;

(b) coating the surface of said first layer with an antistatic material comprising an electron  
20 beam curable mixture;

(c) curing said antistatic material by exposing it to an electron beam;

25 (d) providing a second layer of a flexible plastic material having primary and secondary major surfaces with an electrically conductive material deposited on said primary major surface;  
30

(e) joining said first and second layers along the primary major surfaces of said second layer and said second ply of said first layer by coating  
35 one or both of said primary major surfaces and said second ply with an adhesive and pressing said first and second layers together; and

40 (f) curing said thermosetting adhesive by exposing it to an electron beam, said curing steps



0219315

causing said antistatic material to provide  
antistatic properties to both of said layers.

25. The method of Claim 22 or 24 in which  
5 said thermosetting adhesive and said antistatic  
material are blended together and coated  
simultaneously in steps (b) and (e) and are cured  
10 simultaneously in steps (c) and (f).

15

20

25

30

35

40

34,157A-F

10 11 00

1 / 5

0219315

Neu eingereicht / New filed  
Nouvellement d'après

FIG-1




FIG-2




FIG-3




FIG-3A




FIG-4




FIG-5




FIG-6




FIG-7





FIG-8



12

# **EUROPEAN PATENT APPLICATION**

21 Application number: **86307816.8**

22 Date of filing: **09.10.86**

51 Int. Cl.: **B 32 B 7/02, H 05 F 1/02,  
H 01 L 23/56, B 65 D 31/02**

30 Priority: **09.10.85 US 785808**  
**29.05.86 US 868824**

43 Date of publication of application: **22.04.87**  
**Bulletin 87/17**

24 Designated Contracting States: **AT BE CH DE ES FR GB**  
**IT LI NL SE**

88 Date of deferred publication of search  
report: **13.04.88 Bulletin 88/15**

71 Applicant: **THE DOW CHEMICAL COMPANY, 2030 Dow**  
**Center Abbott Road P.O. Box 1987, Midland,**  
**MI 48640 (US)**


72 Inventor: **Mott, Charles L., 5111 Perrine Road, Midland**  
**Michigan 48640 (US)**

74 Representative: **Raynor, John et al, W.H. Beck, Greener**  
**& Co 7 Stone Buildings Lincoln's Inn, London WC2A 3SZ**  
**(GB)**

54 **Antistatic sheet material, package, and method of making.**

57 A flexible sheet material and package formed therefrom is provided. The multilayer sheet material includes a first flexible heat sealable plastic (30) material with antistatic properties on at least the one major surface (32) thereof which first layer is laminated to a second flexible plastic material (38) with an electrically conductive material (44) on the one major surface (40) thereof and antistatic properties on the other major surface (42) thereof.

The multilayer sheet material can include a first inner flexible, heat sealable layer having antistatic properties or intermediate layer having electrically conductive material thereon, and an outer layer of an antistatic material. Additional layers may be added.



**EP 0 219 315 A3**



European Patent  
Office

# EUROPEAN SEARCH REPORT

0219315

Application Number

EP 86 30 7816

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
D,A	US-A-4 424 900 (R.J. PETCAVICH) * Claims 1,7-14; column 2, line 16 - column 3, line 55; figures 1,2 *	1,3,5,6 ,9,10, 13,14, 17,20, 23	B 32 B 7/02 H 05 F 1/02 H 01 L 23/56 B 65 D 30/08
D,A	GB-A-2 156 362 (KING-SEELEY THERMOS CO.) * Claims 1-5,9,14-18; page 1, line 39 - page 3, line 16; examples 1-3,5-9 *	1-3,8,9 ,13,14, 17-19, 22,23	
A	US-A-3 572 499 (R.L. MONDANO) * Claims 1-8; column 1, line 28 - column 3, line 7; figures 1-3 *	1-3,5- 10,13- 17,20	
A	EP-A-0 114 802 (CHEMIEFASER LENZING AG) * Claims 1,3-7,9,10; page 3, lines 15-32; page 5, line 9 - page 8, line 13 *	1-5,8- 10,13, 14,17, 20	
			TECHNICAL FIELDS SEARCHED (Int. Cl.4)
			B 32 B H 05 F H 01 L B 65 D
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 08-01-1988	Examiner BLASBAND I.
<b>CATEGORY OF CITED DOCUMENTS</b> X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/82 (P0401)